





G101 G203 G112 G113 G616



G205 G206 G211 G212 G254




S262 S265 S301 S376 S509



S351 S352 S100 S112 S218



H107 H108 H115 H169 R267



R312 R109 R103 R161 R179



R119 P016-COAST SAND P019-RAVEN CINZA M43-BRISTOL GREY M42-CAFE BROWN



M09-TURKEY GOLD M12-PEARL AZUL M14-AMAZON BROWN M15-MADISON GREY M16-BROWN CRYSTAL




V01-ARLINGTON



V02-BURLINGTON




V03-DOVER



V04-GEORGETOWN



V05-HUDSON



V06-KINGSTON



V07-MILTON



V08-NEWPORT



V09-OAKLAND



V10-RIVERSIDE



V11-SALEM



V12-WINCHESTER

TECHNICAL DATA

Technical Specifications*		
TEST PERFORMED	TEST PROCEDURE	TEST RESULTS
Specific Gravity	ASTM C97	2.45gr/cm
Mohs Hardness	BS 6431	6-7 Mohs
Impact Resistance	TSEN 14617-9	15-25cm for 1.2cm products
Impact Resistance	TSEN 14617-9	35-60cm for 2cm products
Impact Resistance	TSEN 14617-9	80-175cm for 3cm products
Flexural Strength	TSEN 14617-2	40-70 N/m ²
Flexural Strength	ASTM C880	6301 psi
Abrasion Resistance	TSEN 14617-4	140-175mm
Water Absorption	TSEN 14617-1	0.1%
Water Absorption	BS 6431-11	0.1%
Flame Spread	ASTME-84	Class-A
Chemical Resistance	ASTMD2299	Only strong acids amd bases may affect
Chemical Resistance	BS 6431-18	
Resistance to Freeze and Thaw Cycling	ASTM C1026	No change
Modulus of Rupture	BS 6431-12	52.4 N/mm ²
Thermal Shock Resistance	ASTM-C484	No visible defects
Wheathering	ASTM-G23	No visible changes after 100 hours
*Test results may vary according to product properties.		

TufBuilt[®]

Affordable Building Products LLC

4002 Ross Lane, Chanute, KS 66720

Tel: 877-SEEK-TUF (877-733-5883)
Fax: 877-346-8744 www.tufbuilt.com

TufBuilt[®]

Affordable Building Products LLC

Quartz Catalogue

